

Härtevergleichstabelle für Toolox® und Hardox®

Zugfestigkeit MPa	715	790	820	861	935	995	1011	1090	1169	1245	1328	1412	1494	1580	1758	1940	2130
Vickershärte HV	205	233	243	261	289	311	317	345	373	401	429	458	485	514	569	627	682
Brinellhärte HBW	225	250	260	275	300	320	325	350	375	400	425	450	475	500	550	600	650
Rockwell HRC	19	22,5	24	26	29	32	32,5	35,5	38	40	42,5	44,5	46,5	49	52,5	55	57,5

